

Data Sheet

PK #1

Manufactured by: Berry Plastics Corporation
Tapes and Coatings Division
918 8th Avenue
Columbus, GA 31902
706.323.5970

Specification: MIL-PRF-121, Type 1

Properties	Test Method	Unit of Measure	Typical Value
Tensile Strength MD/XMD	ASTM-D-882	lbs at break	10.0/30.0
Tear MD/SMD	ASTM-689	g	160.0/200.00
Burst	Mullen	psi	50
Seal Strength @ 520 F; 60psi; 3/4 sec	ASTM-D-882	lbs/in	4.0
Caliper		mils	~7.0
Yield		sq in/lb	4965

Disclaimer

The data presented refers to typical values only and should serve only as a guide and does not encompass normal variability, or constitute any warranty. We urge purchasers to conduct tests for suitability in their specific end use.

 **MidSouth**
PACKAGING INC.

P O BOX 42000

MEMPHIS, TN 38174

PH: 901.276.0646 FAX: 901.276.0294

EMAIL: sales@midsouthpackaging.com