

# Data Sheet

## PK #18

Manufactured by: Berry Plastics Corporation  
Tapes and Coatings Division  
918 8th Avenue  
Columbus, GA 31902  
706.323.5970

### Specification: MIL-PRF-121G, Type 2

Properties	Test Method	Unit of Measure	Typical Value
Tensile Strength MD/XMD	ASTM-D-882	lbs at break	29.0/20.0
Tear MD/SMD	ASTM-689	g	140./130.0
Burst	Mullen	psi	45.0
Seal Strength @ 520 F; 60psi; 3/4 sec	ASTM-D-882	lbs/in	4.0
Caliper		mils	~5.5
Yield		sq in/lb	6447

#### Disclaimer

The data presented refers to typical values only and should serve only as a guide and does not encompass normal variability, or constitute any warranty. We urge purchasers to conduct tests for suitability in their specific end use.

 **MidSouth**  
PACKAGING INC.

P O BOX 42000  
MEMPHIS, TN 38174

PH: 901.276.0646 FAX: 901.276.0294  
EMAIL: [sales@midsouthpackaging.com](mailto:sales@midsouthpackaging.com)