

Data Sheet

PK #1

Manufactured by: Berry Plastics Corporation
Tapes and Coatings Division
918 8th Avenue
Columbus, GA 31902
706.323.5970

Specification: MIL-PRF-121, Type 1

| Properties | Test Method | Unit of Measure | Typical Value |
|--|-------------|-----------------|---------------|
| Tensile Strength MD/XMD | ASTM-D-882 | lbs at break | 10.0/30.0 |
| Tear MD/SMD | ASTM-689 | g | 160.0/200.00 |
| Burst | Mullen | psi | 50 |
| Seal Strength @ 520 F; 60psi; 3/4 sec | ASTM-D-882 | lbs/in | 4.0 |
| Caliper | | mils | ~7.0 |
| Yield | | sq in/lb | 4965 |

Disclaimer

The data presented refers to typical values only and should serve only as a guide and does not encompass normal variability, or constitute any warranty. We urge purchasers to conduct tests for suitability in their specific end use.

 **MidSouth**
PACKAGING Inc.

P.O. Box 36216
Pensacola, FL 32516

Ph: 850.898.3797

Fx: 901.276.0294

sales@midsouthpackaging.com