

Data Sheet

PK #18

Manufactured by: Berry Plastics Corporation
Tapes and Coatings Division
918 8th Avenue
Columbus, GA 31902
706.323.5970

Specification: MIL-PRF-121G, Type 2

Properties	Test Method	Unit of Measure	Typical Value
Tensile Strength MD/XMD	ASTM-D-882	lbs at break	29.0/20.0
Tear MD/SMD	ASTM-689	g	140./130.0
Burst	Mullen	psi	45.0
Seal Strength @ 520 F; 60psi; 3/4 sec	ASTM-D-882	lbs/in	4.0
Caliper		mils	~5.5
Yield		sq in/lb	6447

Disclaimer

The data presented refers to typical values only and should serve only as a guide and does not encompass normal variability, or constitute any warranty. We urge purchasers to conduct tests for suitability in their specific end use.

 **MidSouth**
PACKAGING Inc.

P.O. Box 36216
Pensacola, FL 32516

Ph: 850.898.3797

Fx: 901.276.0294

sales@midsouthpackaging.com