



MarvelSeal 700

Berry Plastics®

Preliminary data - subject to change

APPLICATIONS

- Heavy/lubricated products

FEATURES & BENEFITS

- Excellent barrier
- Strong oil and grease resistance
- Broader seal curve
- Heavy duty
- Very high seal strength
- Excellent puncture resistance
- Berry's strongest laminate meeting Spec 131K

PRODUCT DESCRIPTION

BON/PE/FOIL/EAA/COEX FILM

TEST DATA

Test	Typical Value	Unit of Measure	Test Method
Caliper	6.85	mil	
Tensile MD	35.57	lb/in	ASTMD882
Tensile CD	32.65	lb/in	ASTMD882
Tear MD	273.12	gf	ASTM 689
Tear CD	553.12	gf	ASTM 689
WVTR 3/31*	<.0023	g/100 in ² /day	ASTM F1249
OTR 2/20H**	0.009	cc/100 in ² /day	ASTM D3985
Puncture	9.6	lbs	FED STD 101

*Calculated upper limit from supplier data. Mocon measurements were conducted to validate but were limited to the instrument detection limit of .0023 g/100 in²/day.

** Calculated

The information presented herein was prepared at BERRY PLASTICS CORPORATION (Corporate Office: 101 Oakley Street, Evansville, IN 47710) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.

MS MidSouth
PACKAGING Inc.

P.O. Box 36216
Pensacola, FL 32516

Ph: 850.898.3797

Fx: 901.276.0294

sales@midsouthpackaging.com